8,

Weekly Report of Gold Deposits Melted at United States Mint.

1880

Date.		Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.		Gain. oz.	dec.	Description of Bullion.	Notes of Melter & Refiner. 25/2/80
Feby	16th	330	B. Metzger	16	78	8	50	8	28	48	71			Button, Base	These deposits are from
		1	McCall & Newman	50	78	50	42		36		71			Bar	the following sources:
		2	Drexel & Co.	51	03	51	03							For. Coin	South Carolina 1
		3	G. C. Thompson	20	38	20	52						14	Jewelry & Wtch Cases	Utah 1
		4	A. Loudon Snowden, Supt.	182	72	182	72							U.S. Assay Coin, Strips, &c.	Coin 5
		5	W. H. Lee	42	32	42	30		02		05			Bar	Finer bullion 10
		6	G. C. Thompson	12	57	9	90	2	67	20	54			Jewelry & Wtch Cases	Baser " 5
		7	Do	58	90	48	90	10	00	16	95			Bar, Base	Jewelry, &c. 7
		8	John H. Watt, Cash^r	20	80	19	82		98	4	67			Aml, S.C.	very base 5
		9	Simons, Bro. & Co.	87	74	87	59		15		17			Bars	Total 34
		40	C. & A. Peguignot	57	87	57	95						08	Bar	
		1	Phillips & Jacobs	37	60	37	60							U.S. Coin	The losses on the amal-
		2	Richd Nalms	26	86	26	86							U.S. Coin	gam fr. S. Carolina,
		3	Chas. T. Grill	1	67	1	68						01	Medal	4.67% & from Utah,
		4	S. R. & F. Hansell	5	93	5	60		33	5	50			Aml, Utah	5.50% are quite mod-
	17th	5	G. C. Thompson	21	87	20	82	1	05	4	77			D.Pl., Jewelry, &c.	erate; — on the finer
		6	W. H. Sheafer & Co.	61	52	37	38	24	14	38	94			Buttons, Base	bullion 0.13% mode-
	18th	7	G. C. Thompson	12	80	9	05	3	75	28	85			Ring, Base	rate; — on the baser,
		8	H. T. Lare	20	74	17	12	3	62	17	24			Leaf	4.97% fair; — on the
	19th	9	G. C. Thompson	33	08	25	90	7	18	21	76			Jewelry	Jewelry &c 12.82%
		50	Do	6	43	6	43							Button	nearly up to its general
		1	A. Humbert	44	00	43	98		02		05			Bar	average; — on the very
		2	W. B. Musser	24	08	19	02	5	06	21	08			Wch Cases, Jewelry & D.Pl.	base, 30.14%, rather
	20th	3	G. C. Thompson	31	90	29	91	1	99	6	22			Wch Cases, Jewelry & Bars	above its average
		4	Do	134	50	127	80	6	70	5	00			Bars	The loss on 5 deposits
		5	Do	22	35	22	04		31	1	41			Ring	of coin .00 is rather
		6	Do	11	67	10	67	1	00	8	33			Bar	too low.
		7	Phillips & Jacobs	53	74	53	74							U.S. Coin	J. H. C. Booth
	21st	8	G. C. Thompson	52	74	48	39	4	35	8	21			Crushed Quartz	M. & R.
		9	H. Muhr's Sons	15	33	15	33							Bar	
		60	L. R. Ford	10	71	10	50		21	1	91			Wch Cases	
		1	John Streety	9	35	9	32		03		33			Buttons	
		2	G. C. Thompson	1	48	1	48							Bar	
		3	J. C. White	21	30	18	07	3	23	15	38			Jewelry & D.Pl.	
				1263	54	1178	34	85	43	9	62		23		

For week ending February 21st 1880

Approximate value, $18,264.27

To the Director of the Mint.

J. Robley Dunglison, Register.

RG104 E-1 Box 120

Report of Gold Deposits
melted for week ending
February 21st 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits melted for week ending February 21, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]